



## PTFE Tape

## self adhesive

acc. to ABS 5766 A



Applications	sliding assistance and surface protection		
Material	Polytetrafluorethylene, specially coated, meets the requirements of ABS 5766 A		
Colour	grey		
Dimensions, width <sup>1)</sup>	from 25 mm up to 1200 mm		
Dimension, roll length <sup>1)</sup>	min. 2,5m, depending on thickness		
Thickness <sup>1)</sup>	0.35 mm	0.65 mm	1.0 mm
Peel resistance on CRES	>20 N/25 mm	>20 N/25 mm	>20 N/25 mm
Temperature range	-55 °C up to +85 °C		
Storage Temperature	from -10 °C to 25 °C, (short term exposure 35°C max.)		
Relative humidity:	from 10% R.H. to 70% R.H.		
Shelf life	12 months, when stored in the original package		
Flammability	Test: AITM 2.0002B, Requirement: §25.853(a) & CS/FAR-25 App.F, Part I, §(a)(1)(ii)* *bonded on 0,025mm Aluminiumfoil		
1) Other dimensions and thicknesses are available on request.			



## PTFE Tape

## self adhesive

acc. to ABS 5766 B



Applications:	sliding assistance and surface protection		
Material	Polytetrafluorethylene, specially coated, meets the requirements of ABS 5766 B		
Colour	grey		
Dimensions, width <sup>1)</sup>	from 15 mm up to 1000 mm		
Dimension, roll length <sup>1)</sup>	min. 2.5 m, depending on thickness		
Thickness <sup>1)</sup>	0.15 mm	0.30 mm	0.55 mm
Peel resistance on CRES	>7 N/25 mm	>7 N/25 mm	>7 N/25 mm
Temperature range	-55 °C up to +150 °C		
Storage Temperature	from -10 °C to 25 °C , (short term exposure 35°C max.)		
Relative humidity:	from 10% R.H. to 70% R.H.		
Shelf Life	6 months, when stored in the original package		
Flammability	Test: AITM 2.0002B, Requirement: §25.853(a) & CS/FAR-25 App.F, Part I, §(a)(1)(ii)* *bonded on 0,025mm Aluminiumfoil		
1) Other dimensions and thicknesses are available on request.			